



HOW TO TAKE CARE OF

BEALSTONE®

Although waterproof in the mass and hardwearing, a **BEALSTONE® surface must be protected against stains**, just like a natural stone, as the aggregates that are added can be of different origin.

The maintenance of a BEALSTONE® surface depends mainly on the protection that was applied. For surfaces treated with BIPUR, it is best to use a neutral cleaner.

For surfaces protected with natural products like oil (OIL OH TR®) or wax (BEALWAX), those are more sensitive to acids and fats. For regular maintenance, a sponge or cloth with mild & nourishing soap (without mordant agents) is sufficient, for example a solution of 1 liter of lukewarm water with 1 to 2 spoons of FINISH SA TR well diluted (available at BEAL or its distributors).

Moreover, it is advisable to **treat regularly surfaces with oil (OIL OH TR®) or wax (BEALWAX)** as applicable, in order to «feed» the surface. Impregnate slightly the surface to treat using a cloth, paintbrush or roller. Remove any surplus with a clean cotton cloth to avoid drips on vertical surfaces or extra thickness on horizontal surfaces. Make sure you remove any traces of limescale or other residue beforehand.

In a shower, whatever the coating, limescale will settle after each use, which will cause other residues like soap and dirt to stick. This is why we recommend a weekly cleaning. For the removal of such residues on a BEALSTONE surface, use white vinegar diluted in lukewarm water (1 part vinegar for 2 parts water). Spray and leave for a few moments before wiping with a soft sponge. Start with small concentrations of vinegar and increase according to the quantity of limescale (maximum 2 parts vinegar for 1 part water). **We recommend that you always do a test on a small area beforehand.**



LEGAL NOTICE

These instructions, and, in particular, the recommendations for the application and final use of the products, are provided in good faith and are based on the knowledge and experience that the BEAL Corporation has acquired to date about its products when they have been properly stored, handled and applied under normal conditions. In practice, the differences between materials, substrates and specific conditions on site are such that this information or any written recommendation or advice given do not imply any guarantee of merchantable quality other than the statutory guarantee against hidden defects. Our liability cannot be committed in any way, assuming an application not compliant with our teaching. None of the data and information relating to suitability and application absolve the client from the need to carry out its own verifications and tests. All orders are accepted subject to our current terms and conditions of trading. It is essential that users consult the most recent version of the instructions for the product in question. These will be delivered to them on request.

Beal International s.a.
Rue du Tronquoy 8 | 5380 Fernelmont | BELGIUM
Tel.: +32 (0) 81 83 57 57 | Fax: +32 (0) 81 83 57 67
info@beal.be - www.bealinternational.com
VAT: BE 0414 592 153

